

Calsperse CS-P25

M & G Mixing Technologies Sdn Bhd (319725T)

PT51682, Kawasan Perindustrian Taman Meru,

30020, Jelapang, Ipoh, Perak

Tel:605-525 2428, Fax:605-525 4648

Email: sales@mgmixing.com.my

Former Release Agent – powder free glove applications

PRODUCT DESCRIPTION

Calsperse CS-P25 is a Calcium Stearate based dispersion specially formulated for the special antitack properties that is required in latex glove manufacturing applications. It is easily miscible with water and no vigorous stirring is required to dilute to required percentage for use in the coagulant tank together with calcium nitrate for powder free gloves manufacture –especially for NR latex gloves production, while it also can be used in NBR gloves as former release agent.



APPLICATIONS

It can be used as release agent in powder free Latex Gloves, condoms, uncured rubber compounds eg retreads, injection or moulded rubber products (Cycle tire) etc.,

Calsperse CS-P25

(former release agent – powder free coagulant)

FEATURES

- ★easily miscible with water
- ★Ease of use

BENEFITS

- ★ Reduced formulation cost
- ★ Improved antitack properties

TYPICAL PROPERTIES

<i>pH (3%)</i>	<i>8.0 -13.0</i>
<i>Physical Form</i>	<i>Milky white to Off white liquid</i>
<i>Specific Gravity</i>	<i>0.90 – 1.04</i>
<i>Viscosity -cps</i>	<i>10 – 1000, sp #62; 100rpm</i>
<i>Total Solids</i>	<i>25 +/- 2.0%</i>

CLASIFICATION

<i>Molecular Formula</i>	<i>Stearic Acid Calcium Salt</i>
<i>CAS No.</i>	<i>1592-23-0</i>

PACKING

It is packed in 200 kg open top HDPE/PP drums or IBC Tanks of 1,000kg

STORAGE

*Store in cool, dry conditions and keep away from direct heat source and sunlight.
When not using the material always seal the packing.*

SHELF LIFE

At least 6-9 months when stored in sealed packing under above mentioned conditions.

DISCLAIMER

The information contained herein is to the best of our knowledge accurate and current and is given in good faith without warranty. Users are deemed to have satisfied themselves in independently as to the suitability of our products for their particular purpose. In no event shall M&G be liable for consequent or incidental damages.

Tel +605-525 2428
Fax +605-528 4648
E-mail: sales@mgmixing.com.my